

Thermal Lamination Film BOPP Silky Matte

Description

It is BOPP based, one side silky matte and both side treated thermal laminating film. Film has extrusion coated surface with low temp. melting resin, which enables the lamination of film to paper products by heat and pressure.

Features

- Silky satin finish
- Excellent resistance to elongation & tear
- Yellow tint free appearance of roll
- Fibre-tear bond strength with paper

Applications

- Thermal lamination with all kinds of printed & unprinted paper and paper boards like book covers, posters, magazines, diaries, brochures, manuals, folders, magazines, photo albums etc.

Special Instructions

- Cosmo thermal Silky Matte film can be laminated with the temperature range of 100 to 120 deg C. However the optimum conditions may be selected based on the lamination speed (Dwell time) and dimensional stability.
- Please make sure that the printed surface is well dried before lamination.
- Strongly recommend to handle with care and cleanliness as it may spoil it's look by rough handling, dust contamination and scratches.
- It is advisable to cool sufficiently one surface before proceeding the lamination to other surface.

Typical Values

Properties	Units	Astm # / Test Method	27 PCT-2 (M-SIL) DL
Unit Weight	g/m ²		22.5
Yield	m ² /kg	D - 4321	44.4
Surface Tension (min.)- Ex-coated side	dynes/cm	D - 2578	40
Un-Coated			40
Gloss (45°) - Un-Coated side	gardner	D - 2457	17 - 25
Lamination Temp.	°C	D - 1204	100 - 120

Updated as on Oct - 2016

Disclaimer : The information provided above is based on COSMO FILMS LTD's conclusive tests, which are indicative only and provided as guidelines. They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.

Cosmo Films Limited

B-14/8-9, MIDC Industrial Area, Waluj, Aurangabad - 431 136, India, T: +91 240 6660000,
1008,DLF Tower -A, Jasola District Centre, New Delhi - 110 025, India, T: + 91-11-49 49 49 49,
E-mail: sales.enquiry@cosmofilms.com